

VENKRAFT PAPER MILLS



Absorbent Kraft Paper

- Highly Absorbent Kraft Paper
- Basis Weights 50 to 180 GSM



At a level of almost 100,000 tons annually, Venkraft is one of the largest producers of containerboard/kraft paper/semi sack kraft paper/Absorbent Kraft Paper in Southern India. Our Four-driner Combined Paper Machine has all the requisite equipments to manufacture the following.


Machine Finished Kraft Paper


GSM Range: 50 to 180 grams/m²

Machine Deckle: 275 to 285 cms. / 108 to 112 inches

BF Range: 18 to 24 BF

Absorbent Kraft Paper is manufactured with high absorbent properties with no sizing. The paper is manufactured to absorb as much resin as possible in the laminates manufacturing process.





Absorben Kraft (TECHNICAL SPECIFICATIONS)

- Highly Absorbent Kraft Paper
- Basis Weights 50 to 180 GSM

Parameter	Unit	Value
Grammage	GSM	100 to 120
Klemms absorbency	Mm/4min	14-22
ASH Content	%(max)	10
Moisture	%(max)	6
C.O.P	(Sec)	25 to 60
PH	% Hydrogen ion	7 to 8
		Tolerance:± 3%

Parameter	Unit	Value
Grammage	GSM	150 to 160
Klemms absorbency	Mm/4min	22-30
ASH Content	%(max)	10
Moisture	%(max)	6.0
C.O.P	(Sec)	35 to 80
PH	% Hydrogen ion	7 to 8
		Tolerance:± 3%

Please note:

- 1. The tolerances are based upon 95% confidence limit and on laboratory results of random samples from mill.
- 2. The specifications are subject to change without any prior notice.
- 3. Moisture is measured on oven dry method.
- 4. Paper board Machine Deckle: 275 cms to 285 cms.

<u>Venkraft Paper Mills Pvt Ltd., Unit – 1</u>

<u>Kraft Unit – Factory Address:</u> 10th K.M.,Kelamangalam Road, Aggondapalli Village, Hosur-635110,

Tamil Nadu, India.

Domestic Marketing Contacts: Email: marketing1@venkraft.com, Marketing Head (+ 91 9442229773),

Tamil Nadu Coordinator (+91 7867004081). Karnataka Coordinator (+91 9600772211).

Export Marketing Contacts: Email: exports@venkraft.com, Export Coordinator (+ 91 8220005701).

www.venkraft.com